

FIBEROCK® BRAND AQUA-TOUGH™ AR INTERIOR PANELS



FEATURES & BENEFITS

Gypsum-fiber abuse-resistant panels outperform paper-faced gypsum board in abuse-prone areas

- Aqua-Tough™ panels provide increased resistance to moisture and mold
- No face paper to scratch or tear
- Resist denting, breaking and puncturing, even in high-traffic areas
- Provide excellent fire resistance
- Offer an economical alternative to concrete block and plaster construction
- Ideal for institutional, commercial and residential interiors
- Certified, recycled content of 97 percent

DESCRIPTION

USG Fiberock® Brand Aqua-Tough™ AR Interior Panels are engineered to provide increased resistance to moisture, mold, abrasion, indentation and penetration for interior walls and ceilings in demanding construction applications. These Gypsum-fiber panels are designed to outperform paper-faced gypsum board. Strong, solid and durable, they are approved for use in wet areas, including residential showers and tub surrounds. They also resist denting, breaking and puncturing—even in high-traffic areas. USG Fiberock Aqua-Tough AR Interior Panels are code approved for use in noncombustible construction. They have exceptional surface-burning characteristics (ASTM E84, Flame Spread 5, Smoke Developed 0) and fire resistance (ASTM E119). 15.9mm. USG Fiberock® Brand Aqua-Tough™ AR Interior Panels may be used in lieu of Type X gypsum panels in over 50 fire-rated wall assemblies as listed in the Underwriters Laboratories Inc. (UL) Fire Resistance Directory under “Type FRX-G.”

TECHNICAL DATA

Property	Unit of Measure	ASTM Test Method	15.9mm USG Fiberock® Brand Aqua-Tough™ AR Interior Panel	12.7mm USG Fiberock® Brand Aqua-Tough™ AR Interior Panel
Flexural Strength	lbf	C473	> 155	>110
Compressive Strength	psi	n/a	> 500	>500
Nail-Pull Resistance	lb (10 mm head diameter, dry)	C473	> 145	>120
Weight	kg/m²	C473	15.1	11.7
Mold Resistance	-	D3273	10 (no growth)	10 (no growth)
Surface-Burning Characteristics	flame/smoke	E84	5/0	5/0
Thermal	“R”/k value	C518	-	30/1.84

Compliance with Standards: Meets ASTM C1278. Edge Configuration: Long edges tapered; ends cut square

ABUSE-RESISTANT PERFORMANCE

ASTM C1629 Performance	Units (pcs.)
*Abrasion	Level 1
Indentation	Level 1
Soft Body Impact	Level 2
Hard Body Impact	Level 1

* With a standard primer and two coats of finish paint, USG Fiberock® Brand Aqua-Tough™ AR Interior Panels will achieve level 3 abrasion resistance.

ADVANTAGES

Abuse Resistant: Engineered to provide increased resistance to abrasion, indentation and penetration, this panel outperforms paper-faced or glass mat-faced panels, with no paper face to tear or scratch.

Water Resistant: Water resistant through the core and suitable for use in wet areas including residential showers and tub surrounds.

Mold Resistant: In independent lab tests per ASTM D3273 Standard Test Method for Resistance to Growth of Mold on the Surface of Interior Coatings in an Environmental Chamber, USG Fiberock Aqua-Tough AR Interior Panels earn the highest score: 10.

Fire Resistant: Superior fire resistance and exceptional surface-burning characteristics. The 15.9mm panel is UL Classified for fire resistance (FRXG) and listed in more than 50 UL wall designs.

Finishing Flexibility: Features a smooth, paintable surface that can also be finished with ceramic tile.

Environmentally Friendly: Made from 97% recycled materials.

LIMITATION

1. USG Fiberock® Brand Aqua-Tough™ AR Interior Panel are designed for interior use only.
2. Panels may be attached to wood or steel-stud framing and furring channels.
3. For abuse-resistant or fire-resistant construction, 20-gauge or heavier studs are required.
4. For improved abuse-resistant system performance, USG ME Metal Beads and Trims or USG Sheetrock® and Beadex® Brand Paper-Faced Metal Corner Bead and Trim and USG Sheetrock® Brand Tuff-Hide™ Primer-Surfacer are recommended.
5. Where USG Fiberock® Brand interior panel systems abut or intersect dissimilar construction or building structural components, isolation techniques, such as caulk and/or slip tracks, are required.
6. USG Control joints should be spaced at a maximum of 8.5 m o.c. in walls and above door jambs; 8.5 m o.c. in ceilings (15m with perimeter relief) and at L-, T- or U-intersections. Location of control joints is the responsibility of the professional/architect.
7. Framing members should be straight and true. Studs and joints must be in true alignment; bridging, firestops, etc. must not protrude beyond plane of framing. Due to strength and rigidity of USG Fiberock interior panels, it may be difficult to compensate for out-of-plane imperfections in framing.

STORAGE OF MATERIALS

All materials shall be delivered in their original unopened packages and stored in an enclosed shelter providing protection from damage and exposure to the elements. All materials should be stored flat

INSTALLATION

1. Position all ends and edges of all gypsum-fiber panels over framing members, except when joints are at right angles to framing members, as in perpendicular application or when end joints are back-blocked.
2. Install panels vertically whenever possible. For horizontal panel application, panels must be gapped 1.6 mm. End joints should be loosely fit. Install panels a minimum of 10 mm. above the floor. To minimize end joints, use panels of maximum practical lengths. Stagger end joints in successive courses with joints on opposite sides of a partition placed on different studs.
3. Attach panels to framing supports by: standard single nailing method, double nailing method, or power-driven screws. Space fasteners not less than 10 mm. from edges and ends of panels and drive as recommended for specified fastening method. Drive fasteners in field of panels first, working toward ends and edges. Hold panel in firm contact with framing while driving fasteners. Drive fastener heads slightly below surface of gypsum-fiber panels in a uniform dimple.
4. Concealment of joints, fasteners and trims in areas that will be painted: For taping use USG Sheetrock® Brand Paper Joint Tape with USG Sheetrock® Brand Durabond® Joint Compound. For finishing use a USG Sheetrock® Brand All Purpose Joint Compound. In areas that will be tiled, finish joints with USG Durock™ Brand Tile Backer Tape and latex-fortified mortar or Type I mastic.
5. For non-fire-rated partition designs, refer to the table below for fastener spacing. For UL fire-rated partition designs, refer to the specific UL design for proper fastener spacing.

SURFACE TREATMENT

Ceilings (Steel-Framed)

Thickness	Application	Frame Spacing	Fastener Spacing	
			Nails	Screws
12.7 mm	Parallel	400 mm o.c.	Level 1	400 mm o.c.
12.7mm	Perpendicular	400 mm o.c.	Level 1	400 mm o.c.
15.9 mm	Parallel	400 mm o.c.	Level 2	400 mm o.c.
15.9 mm	Perpendicular	600 mm o.c.	Level 1	600 mm o.c.

Walls

Thickness	Frame Spacing*	Fastener Spacing	
		Nails	Screws
12.7 mm	600 mm o.c.	200 mm o.c.	300 mm o.c.
12.7mm	400 mm o.c.	200 mm o.c.	400 mm o.c.
15.9 mm	600 mm o.c.	200 mm o.c.	300 mm o.c.
15.9 mm	400 mm o.c.	200 mm o.c.	400 mm o.c.

6. Install trim at all internal and external angles formed by the intersection of either panel surfaces or other surfaces. Apply (metal) (paper-faced) corner bead to all vertical or horizontal external corners in accordance with manufacturer's directions.

USG Fiberock interior panels must be surface treated with one of the options, in accordance with USG ME recommendations. Option A may be used when surface uniformity is not of concern, (i.e., the surface uniformity stipulation has been waived by the job managerial and/or inspection authorities and conditions described in Option B (below) do not exist.)

OPTION 1:

Apply a skim coat of joint compound at a trowel-applied consistency to entire surface and let dry using a USG Middle East Sheetrock® Brand ready-mix all purpose type joint compound.

Note: When properly prepared as a skim coating material, these ready mixed joint compounds can be used in a skim coat operation.

The skim coated surface must be smooth and free of tool marks and ridges (a light sanding of the skim coating may be necessary to remove tool marks). Remove sanding dust from surface, then apply one coat (5-10 mils Wet Film Thickness) of USG Middle East Sheetrock® Brand ready-mix all purpose type joint compound over the entire surface. Allow surface to dry prior to decorating.

Note: A single full coverage coat of USG Sheetrock® Brand Tuff-Hide Primer-Surfacer may be used in lieu of a skim coat of joint compound and the application of USG Sheetrock® Brand First Coat Primer.

OPTION 2:

Recommended in areas where one or more of the following conditions exist:

- 1) Exposure to critical/severe lighting.
- 2) Paints with sheen levels other than flat are specified.
- 3) High value spaces exist.
- 4) Final surface smoothness and uniformity are expected and/or specified.

Apply two separate skim coat of joint compound at a trowel-applied consistency to entire surface and let dry using a USG Middle East Sheetrock® Brand ready-mix all purpose type joint compound.

Note: When properly prepared as a skim coating material, these ready mixed joint compounds can be used in a skim coat operation.

The skim coated surface must be smooth and free of tool marks and ridges (a light sanding of the skim coating may be necessary to remove tool marks). Remove sanding dust from surface, then apply one coat (5-10 mils Wet Film Thickness) of USG Middle East Sheetrock® Brand ready-mix all purpose type joint compound over the entire surface. Allow surface to dry prior to decorating.

Note: A single full coverage coat of USG Sheetrock® Brand Tuff-Hide Primer-Surfacer may be used instead of the second skim coat.

SURFACE TREATMENT

Veneer Plaster

Joints should be treated with USG Sheetrock® Brand Paper Joint Tape and USG Durabond® Joint Compound. Joint surfaces must be treated with a separate coat of joint compound to fully conceal the paper tape. When the joint is completely dry, treat entire wall surface with USG plaster bonder according to application directions. Then apply USG Diamond® Veneer Basecoat Plaster from 1.6 mm to 2.4 mm. thickness using a scratch and double-back technique. This is accomplished by applying a light, thin coat over the entire area, and immediately doubling back with plaster from the same batch to achieve full thickness. When basecoat plaster is firm, broom the surface to leave it rough and open for finish. With basecoat set and partially dry, apply USG Imperial® Veneer Finish Plaster using a scratch and double-back technique. Complete finishing when material is firm. Leave finished surface smooth and dense for decorating.

Ceramic Tile Applications

USG Fiberock® Brand Aqua-Tough™ AR Interior Panels are acceptable for use as a ceramic tile backer.

1. USG Fiberock® Brand Aqua-Tough™ AR Interior Panels are designed for interior use only and should not be used in exterior applications.
2. Panels should not be exposed to sustained temperatures in excess of 50 °C.
3. For fire-resistant or abuse-resistant construction over steel framing, a minimum of 20-gauge steel framing is required.

Notice:

As we are involved in constant products development; this document information is subject to change without prior notice. Please always refer to usgme.com for the updated products information document.

©2020 Factory of USG
Middle East LTD. Co.
All rights reserved.

USG BORAL
INNOVATION INSPIRED BY YOU.™