

# MONOSILENT SPRAY APPLIED FINISH



## FEATURES & BENEFITS

### Fine-textured finish for USG Monosilent Acoustical Plasterboard Ceiling

- Acoustically transparent, technologically advanced formulation
- White color with a fine, granular texture
- High light reflectance (LR-85%)
- 17L pail
- Quick drying, re-coat in 20 to 40 minutes\*
- Applied with pneumatic spray equipment for economical installation

### Notes

\* In less than ideal drying conditions (colder weather), you may have to wait 60-90 min between coats. Check surface is dry to the touch before spraying subsequent coats.

### USE

Designed specifically as the fine-textured finish for USG Monosilent Acoustical Plasterboard Ceiling.

### BASIC INSTALLATION DATA

For complete installation instructions, Refer to USG Monosilent Acoustical Plasterboard Ceiling Installation Guide.

### MIXING

- Finish must be thoroughly mixed prior to application
- Mix in the 17L container prior to filling the spray machine hopper
- Check for proper consistency using the material thickness gauge provided by the spray equipment manufacturer (small steel ball). If the ball sinks completely, the texture is ready to spray. If the ball does not sink within 3-4 seconds, add more water, 100ml at a time, and mix thoroughly until the ball sinks
- Up to 500ml clean, potable water may be added in order to achieve the proper spray consistency

### RECOMMENDED SPRAY EQUIPMENT

A texture sprayer, an air compressor, and a spray gun will be needed to apply the USG Monosilent Spray-Applied Finish over the USG Monosilent Acoustical Plasterboard Ceiling. Equipment specifications are detailed in the USG Monosilent Acoustical Plasterboard Ceiling Installation Guide.

### APPLICATION

In order to achieve proper sound performance and appearance, the finish must be applied in a minimum of two cross-hatch pass coats.

- Apply each coat very lightly with 900mm gun clearance
- Start in one corner and work progressively across the ceiling
- Immediately cross-hatch. Once the finish is dry to the touch (approximately 20 to 40 minutes), re-coat using the same technique
- Apply successive coats until the desired appearance is achieved. After the final coat, wait 24 hours and then remove any minor irregularities with a squeegee trowel
- The finish can be applied directly to bare metal, primed metal, and plastic beads and trims. Maintain proper job site conditions and wear proper protective equipment (safety goggles, respirator, coveralls) while applying texture

### LIMITATIONS

1. For use only with USG Monosilent Acoustical Plasterboard Ceiling panels.
2. Not for use in areas subject to surface contact.
3. Cannot be painted without negatively affecting acoustical performance code requirements.
4. Cannot be applied directly to metal with powder-coated finishes without proper surface preparation.

## PRODUCT DATA

	Monosilent Spray Applied Finish
Color	White LR-85%
Binder	Water-based Acrylic
Coverage	Approximately 18m <sup>2</sup> per 17L pail
pH	9.0 to 10.0
Weight Solids	80%
Packaging	17L pails
Drying Time	Can be re-coated after 20 minutes at 24°C/ 50% R.H. conditions. Drying time is dependent on temperature, humidity, and film thickness.
Storage	Close container after each use. Store in a dry place with moderate temperatures. Protect from freezing. Shelf life is up to 12 months under good storage conditions.

## REFERENCES

For further health and safety instructions, refer to the Safety Data Sheet (SDS) for this product, available from your USG Middle East sales office or **USGme.com**

### Notice:

As we are involved in constant products development; this document information is subject to change without prior notice. Please always refer to **usgme.com** for the updated products information document.

©2022 Factory of USG Middle East LTD. Co.  
All rights reserved.